

FORMICA® LAMINATE BY FORMICA GROUP



POSTFORMING TECHNICAL BRIEF

CONDITIONS AFFECTING POSTFORMING

Successful postforming is easily accomplished by using various techniques which recognize and moderate the common variables associated with postforming. These techniques incorporate preconditioning, temperature control, elimination of drafts, and proper equipment adjustment and maintenance.

PRECONDITIONING

Postforming grade laminate is hygroscopic; that is, it is capable of losing or absorbing moisture from the atmosphere. Therefore, if it is exposed to dry air conditions, a loss of moisture can result that adversely affects its postforming properties. To assure proper postforming performance, Formica® Brand postforming grade laminate should be preconditioned prior to use for at least 48 hours at 70°F (21°C) and 50% relative humidity. Small shop areas can be economically humidified with portable humidifier units. Larger areas may require specific recommendations from an HVAC equipment supplier.

Remember, when seasonal changes approach, preconditioning practices should be observed to maintain consistent postforming conditions inside the shop, regardless of the atmospheric conditions outside. This is especially important during winter months, when dry air conditions often exist.

TEMPERATURE CONTROL

The optimum postforming temperature for Formica® Brand Laminate is at or near 325°F (163°C). Lower temperatures may cause cracking while higher temperatures may cause gloss changes, blistering and/or cracking. If either occurs, alter the surface temperature accordingly. On most equipment this can be accomplished by adjusting the power input to the heater, the heater height or the line speed.

To determine the surface temperature of laminated plastic, there are two primary techniques which can facilitate equipment setup.

One relatively simple technique involves the use of temperature indicators such as Tempilaq® Temperature Indicating Liquid or Tempilstik® Temperature Indicating Crayons to facilitate equipment setup. Another effective method of monitoring and measuring the laminate surface temperature is to use a non-contact infrared thermometer.

ELIMINATE DRAFTS

Avoid open windows or doors near the postforming operation. Sudden drafts over the heated laminate surface can drop its temperature below optimum conditions and cause cracking or crazing. This is especially important during cold weather, when cold blasts from open doors, etc., can happen unexpectedly. The use of temporary or permanent partitions to eliminate drafts is often required.

EQUIPMENT INSPECTION

Commercial or custom-built postforming equipment will perform efficiently and properly only if it is in good working condition. All equipment should, therefore, be inspected periodically. Automatic timers may malfunction. Heating elements may develop hot spots or fail to heat up. Guides or stops may loosen. Rollers may become misaligned or worn. Planned periodic inspection of all critical components will help avoid costly material damage and loss of valuable production time.

COMMON POSTFORMING PROBLEMS

SYMPTOM: CRACKING, CRAZING

PROBLEM	CAUSE	CORRECTION
Heat source	Insufficient heat	Increase heat or rate of heat-up
	Improper heater position	Adjust heater to focus on bend area
Cores	Irregular radius	Sand core
	Poor machining	Check cutter alignment
	Cold cores	Store at 65°F (18°C) minimum
	Contaminated or dusty cores	Clean prior to forming
	Radius too tight	Increase radius
Equipment	Poor alignment	Align equipment
	Dirty equipment	Clean equipment
Laminate	Wrong grade	Use proper grade
	Dry conditions	Humidify storage area

SYMPTOM: BLISTERS

PROBLEM	CAUSE	CORRECTION
Heat source	Too much heat	Reduce heat

SYMPTOM: GLUELINE DELAMINATION

PROBLEM	CAUSE	CORRECTION
Heat source	Insufficient heat to soften laminate	Increase heat
	Too much heat	Reduce heat
Core	Radius too tight	Increase radius
Equipment	Poor alignment	Align equipment
Adhesive	Insufficient adhesive	Increase spread rate
	Improper adhesive	Consult manufacturer
Drying Oven	Insufficient drying time	Increase drying time or oven temperature

SYMPTOM: GLOSS CHANGE

PROBLEM	CAUSE	CORRECTION
Heat source	Too much heat	Reduce heat

FORMICA® LAMINATE BY FORMICA GROUP



POSTFORMING TECHNICAL BRIEF

LIMITED WARRANTY

Formica Corporation expressly warrants that, for a period of one (1) year from the date of first sale, these products will be reasonably free of defects in materials and workmanship, and that when properly handled and fabricated, will conform, within accepted tolerance, to applicable manufacturing specifications. Colors subject to dye lot variations. This limited warranty only applies to Formica® Brand Laminate which is stored, handled, fabricated and installed in the manner recommended by Formica Corporation. Due to the variety of uses and applications to which Formica® Brand Laminate may be put, FORMICA CORPORATION CAN MAKE NO WARRANTY THAT THIS PRODUCT IS SUITABLE FOR ANY PARTICULAR PURPOSE AND CAN MAKE NO OTHER WARRANTIES, EXPRESS OR IMPLIED, OTHER THAN THOSE SET FORTH ABOVE.

DISCLAIMER OF WARRANTIES

THE WARRANTIES SET FORTH HEREIN OR IN FORMICA CORPORATION'S WARRANTY DOCUMENTS WITH RESPECT TO A PRODUCT ARE THE ONLY WARRANTIES MADE BY FORMICA CORPORATION IN CONNECTION WITH THESE PRODUCTS, AND ARE EXPRESSLY IN LIEU OF ANY OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WITHOUT LIMITATION, ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. PRODUCTS SOLD BY FORMICA CORPORATION ARE SOLD ONLY TO THE SPECIFICATIONS SPECIFICALLY SET FORTH BY FORMICA CORPORATION IN WRITING. FORMICA CORPORATION'S SOLE OBLIGATION FOR A REMEDY TO BUYER SHALL BE REPAIR OR REPLACEMENT OF NON-CONFORMING PRODUCTS, OR AT THE OPTION OF FORMICA CORPORATION, RETURN OF THE PRODUCT AND REFUND OF THE PURCHASE PRICE. BUYER ASSUMES ALL RISK WHATSOEVER AS TO THE RESULT OF THE USE OF THE PRODUCTS PURCHASED, WHETHER USED SINGLY OR IN COMBINATION WITH OTHER SUBSTANCES.

LIMITATION OF LIABILITY

No claim by buyer of any kind, including claims for indemnification, whether as to quality or amount of products delivered or for non-delivery of products, shall be greater in amount than the purchase price of the products in respect of which damages are claimed. IN NO EVENT SHALL FORMICA CORPORATION BE LIABLE TO BUYER FOR ANY SPECIAL, INDIRECT, INCIDENTAL, RELIANCE, EXEMPLARY, OR CONSEQUENTIAL DAMAGES OR COVER, OR LOSS OF PROFIT, REVENUE OR USE, IN CONNECTION WITH, ARISING OUT OF, OR AS A RESULT OF, THE SALE, DELIVERY, SERVICING, USE OR LOSS OF USE OF THE PRODUCTS SOLD HEREUNDER, OR FOR ANY LIABILITY OF BUYER TO ANY THIRD PARTY WITH RESPECT THERETO. BUYER SHALL INSPECT FOR NONCONFORMITY PROMPTLY UPON RECEIPT. Failure by buyer to give Formica Corporation written notice of claim within 30 days from date of delivery or, in the case of non-delivery from the date fixed for delivery, shall constitute a waiver by buyer of all claims in respect of such products.

This limited warranty gives purchaser of Formica® Brand Laminate specific legal rights. Other rights may be available and vary from state to state.

Any information or suggestion concerning application, specifications or compliances with codes and standards is provided solely for your convenient reference and without any representation as to accuracy or suitability. Formica Corporation disclaims any legal responsibility. The user must verify and test the suitability of any information or products for their own particular purpose of specific application.

MANUFACTURER

Formica® Brand Laminate sheets are manufactured by Formica Corporation.

TECHNICAL SERVICES

Technical assistance may be obtained through your local Formica® Brand Products Distributor or from Formica Corporation trained representatives in sales offices throughout the country. To assist these representatives, Formica Corporation maintains a sales and technical services staff in Cincinnati, Ohio. For technical assistance, contact your distributor or sales representative; write the company directly at Formica Corporation Technical Services Department, 10155 Reading Road, Cincinnati, OH, 45241; call (513) 786-3578 or 1-800-FORMICA™; or fax (513) 786-3195. In Canada, call 1-800-363-1405. In Mexico, call (525) 530-3135.

Formica is a sublicensed trademark to Formica Corporation. Formica and the Formica Anvil logo are registered trademarks of The Diller Corporation. 1-800-FORMICA is a trademark of The Diller Corporation. The products and manufacturing processes of Formica Corporation are protected under U.S. and foreign patents.

All ® brands are registered trademarks of the respective owners. All ™ brands are trademarks of the respective owners.

For warranty information, please visit www.formica.com or call 1-800-FORMICA™.

©2019 Formica Corporation
Cincinnati, Ohio 45241