

EVERFORM™ SOLID SURFACE



DARK COLOR FABRICATION TECHNICAL BRIEF

Formica Corporation has developed a fabrication technique that will help fabricators improve the appearance of drop edge build-up seams. This fabrication technique will work for all Everform™ Solid Surface designs, but it is critical when working with dark colors.

This technique has been developed to insure the highest quality finished product by minimizing visible (white) seams in drop edge build-up assemblies. During final finishing, in our manufacturing facility, the back of the sheet is sanded using 100-grit sandpaper with a wide belt sander. This process enables us to maintain thickness tolerances and ensures a consistent flat back of the sheet. The back sanding, however, creates whiteness on the back of the sheet that, if not removed, could create a visible seam in drop edge build-ups.

TO ACHIEVE THE BEST POSSIBLE EDGE APPEARANCE WITH DARK COLORS:

- Sand the back side of the countertop deck (in the drop edge area) and sand the face and back of each edge strip with 120-grit (100 micron) sandpaper using a random orbital sander.
- Sand until the white linear lines have been removed from the back of the sheet/strip and the face has been roughed up enough to insure proper bonding.
- Always glue the face of the material to the back of the next piece in the drop edge assembly.
- Use recommended color matched adhesive.

FINISHING DARK COLORS

Formica Corporation fabrication techniques that will help fabricators improve the appearance of the finish in dark colors. These fabrication techniques will work for all Everform™ Solid Surface designs, but it is critical when working with dark colors.

Everform™ Solid Surface sheets, InDepth Surfacing and molded shapes are finished to a satin finish in the factory but fabrication and installation operations, as well as customer selection of other finishes, make it necessary for the fabricator and/or installer to adjust the final finish.

The abrasive mineral of choice for finishing solid surfacing material is aluminum oxide. It is available in various sizes from coarse to extremely fine in either the P-graded grit or micron forms. We recommend using the Micron system for sanding. Below is a chart of the standard grits that are available. 100 micron would be the coarsest and 15 would be the finest on this chart.

MICRON SYSTEM

100 micron	80 micron	60 micron
40 micron	30 micron	15 micron

NON-WOVEN NYLON ABRASIVE PADS

Used for final finishing to matte or satin finish, maintenance, etc. Generally used in two grades:

Maroon: (very fine) for matte finish 3M Scotch-Brite #7447 Mirka® Mirlon #447

Gray: (ultra fine) for satin finish 3M Scotch-Brite #7448 Mirka® Mirlon #448

When sanding dark colors, it is important to not skip the progression of grit or micron. For example it would be incorrect to sand with 100 micron and skip to 60 micron when sanding dark colors. The correct step would be 100 micron, 80 micron, 60 micron.

Always clean thoroughly between sanding steps. Particles from the abrasive pads could be left on the surface, so when the next step of sanding occurs, larger particles will cause “swirls” and create a poor finish.

In most cases, solid surface countertops should be installed with a “matte” finish. This is achieved by sanding to 60 micron and then a maroon abrasive pad 3M Scotch-Brite #7447. To enrich the color of the dark colors, it may require extra steps of sanding. A “satin” finish may be required. To achieve this sand with 100 micron, 80 micron, 60 micron, 30 micron and a gray abrasive pad 3M Scotch-Brite #7448. Sanding wet with the #7448 will create a more uniform finish. The use of a 500 grit Abralon pad made by Mirka also helps bring the color out of a dark color.

There are also many quality manufactures of large profile sanding equipment that will increase your productivity and help you sand to a high quality finish. Gem Industries www.gemindustries.com and Pinske www.pinske-edge.com are just a couple.

COLOR LIST

*DISCONTINUED

307 Spanish Paprika Mist*	704 Saltillo Stone*
309 Pesto Mist*	714 Federal Cornerstone*
389 Marron Graniti*	715 Gothic Cornerstone*
411 Grafite Terrazzo Matrix	763 Coffee Silica*
415 Luna Steel	774 Luna Fossil*
501 Black Lava	775 Luna Storm
650 Ebony Mosaic*	777 Noce Travertine*
651 Chicory Mosaic*	780 Luna Stone
652 Pecan Mosaic*	781 Luna Concrete
654 Botanical Mosaic*	782 Luna Weather
655 Coastal Mosaic*	787 Drift Travertine*
656 River Rock Mosaic	

EVERFORM™ SOLID SURFACE



DARK COLOR FABRICATION TECHNICAL BRIEF

FINISHING EVERFORM™ SOLID SURFACE

Everform™ Solid Surface sheets and molded shapes are finished to a satin finish in the factory but fabrication and installation operations, as well as customer selection of other finishes, make it necessary for the fabricator and/or installer to adjust the final finish.

There are three basic finishes that are used. Each of these have certain advantages and disadvantages which should be seriously considered for each application. The properties of these finishes are described below:

MATTE		SATIN		DARK COLORS		POLISHED	
P-grade	Micron	P-grade	Micron	Micron		Micron	
120	100	120	100	100		100	
180	80	180	80	80		80	
220	60	220	60	60		60	
320	30	320	30	30		40	
3M® Scotch-Brite Maroon #7447		3M® Scotch-Brite Gray #7448		3M® Scotch-Brite Gray #7448 – Wet		30	
				Mirka® Abralon 8A-241-500 – Wet		15	
						9	
						3M® Finesse-it #051144 -77340	
						3M® Finesse-it #051144-81235	

IMPORTANT NOTICE

See www.formica.com for the most current technical data and warranty information, which is the only authorized source for this information.

MANUFACTURER

Everform™ Solid Surface products are toll manufactured in accordance with Formica Corporation's product specifications and quality requirements.

TECHNICAL SERVICES

Technical assistance may be obtained through your local Formica® Brand Products Distributor or from Formica Corporation trained representatives in sales offices throughout the country. To assist these representatives, Formica Corporation maintains a sales and technical services staff in Cincinnati, Ohio. For technical assistance, contact your distributor or sales representative; write the company directly at Formica Corporation Technical Services Department, 10155 Reading Road, Cincinnati, OH, 45241; call (513) 786-3578 or 1-800-FORMICA™; or fax (513) 786-3195. In Canada, call 1-800-363-1405. In Mexico, call (525) 530-3135.

Formica is a sublicensed trademark to Formica Corporation. Formica and the Formica Anvil logo are registered trademarks of The Diller Corporation. 1-800 -FORMICA and Everform are trademarks of The Diller Corporation. The products and manufacturing processes of Formica Corporation are protected under U.S. and foreign patents.

All ® brands are registered trademarks of the respective owners. All ™ brands are trademarks of the respective owners.

For warranty information, please visit www.formica.com or call 1-800 -FORMICA™.

©2020 Formica Corporation
Cincinnati, Ohio 45241